

Firestone

Nylon 6

Processing Information

Listed below are our recommended start up processing temperatures. This data should be considered as a guide and not absolute. We suggest starting at the lower end of the listed temperatures and increase as necessary.

Barrel	Unfilled N6	Reinforced N6
Rear Zone	460-480°F	520-540°F
Center Zone	460-480°F	530-550°F
Front Zone	470-500°F	510-530°F
Nozzle	480-500°F	500-520°F
Melt	480-500°F	520-540°F
Mold Cavity	120-180°F	130-180°F
Drying Conditions:	165°F for 4 hours (when required)	
Suggested Max Moisture	0.12%	

NON WARRANTY. The information presented in this publication is based upon the research and experience of Firestone and is to the best of its knowledge accurate; however, no guarantee of its accuracy is made. Since Firestone has no control over the conditions under which its products may be employed and since information as to the physiological and other properties of its products is incomplete, Firestone cannot guarantee the results obtained and assumes no liability whatsoever for possible damage or injury whether or not caused by following the suggestions in this brochure. Firestone will not be liable for resulting or consequential damage. Firestone warrants that none of its commercial products infringes the claims of any Canadian or United States patent but no license is granted nor recommendation made hereby to practice any invention covered by any patent owned by Firestone or by others.